

ATROX® 800HT5

Electrically and Highly Thermally Conductive Die Attach Adhesive

ATROX® 800HT5 is an ultra-low stress thermosetting conductive die attach adhesive with high thermal conductivity designed for high power exposed pad semiconductors. ATROX® 800HT5 has low resin bleed out and low condensable organics which ensure excellent package reliability.

TYPICAL PROPERTIES

MATERIAL PROPERTIES	METHOD	VALUE	REMARKS
A. Uncured			
Chemical type		Thermosetting	
Color	Visual	Grey	
Viscosity at 25°C at 5.0 RPM	ASTM D2196-99	13,000 cps	Brookfield Spindle 51
Thixotropic index (0.5 RPM/5.0 RPM)	ASTM D2196-99	5.5	Brookfield Spindle 51
Pot Life @ 23°C (time to doubling of viscosity)	ISO 10364:1993	>24 hours	Brookfield Spindle 51
Storage Temperature		-40 (°C/°F)	
Shelf Life @ -40 (°C/°F)		6 months	
B. Cured			
Glass Transition (Tg)	TMA	20°C	
Modulus at 25°C	DMA	1.0 GPa	
Modulus at 260°C	DMA	0.9 GPa	
CTE1 (Below Tg)	TMA	26 ppm	
CTE2 (Above Tg)	TMA	110 ppm	
Thermal Conductivity: Bulk	Laser Flash	75 W/mK	
Volume Resistivity	4-Point probe	0.00002 Ohm-cm	
% Moisture Absorption	72 hrs @ 85%RH/85°C	<0.2	

DIE SHEAR STRENGTH (5 mm x 5 mm Bare Silicon Die)


LEAD FRAME	CURE CONDITION	MEASURING TEMPERATURE	VALUE
Ag	150°C/30 min +200°C/120 min	260°C	13 Kg
NiPdAu (PPF)	150°C/30 min +200°C/120 min	260°C	12 Kg
Cu	150°C/30 min +200°C/120 min	260°C	12 Kg

MATERIAL APPLICATION

ATROX® 800HT5 is formulated to be applied using a time pressure pump equipped on most die bonders. The material should be consistently dispensed over time. Equipment settings need to be optimized for desired material deposition response based on model and configuration.

CURE

ATROX® 800HT5 cures using ramp profile with 30 minute soak at 150°C + ramp to 200°C and soak for 120 minutes. It is recommended that the cure schedule includes at ramp at 5 to 10°C and a controlled cooling cycle to minimize thermal stresses. Alternatively the material can be cured at higher peak temperature such as 250C to enhance the adhesion of the material. Depending on thermal mass of application cure times may vary and should be optimized by the end user.



RELIABILITY PERFORMANCE

ATROX® 800HT5 is recommended for excellent reliability with stable Electrical and Thermal performance during MSL and Thermal Cycling. There is no limitation on die size for metalized OR Bare Silicon die packages. However, it is recommended to consult with AAM Technical Service for optimizing critical parameters for specific packages.

CLEAN-UP

Uncured material may be cleaned from dispenser components and surfaces with a variety of solvents, including IPA, acetone, MEK, methylene chloride, etc. Always wash and dry thoroughly prior to re-use of the dispenser components. The cleaning technique should be active cleaning of the components – flush, wash or wipe, followed by a drying step to ensure a clean, dry surface. Do not soak since this can solubilize the hardener within the uncured resin and curing (very difficult to remove). Contact your equipment supplier to ensure the solvent is compatible with their components. Clean and maintain dispense valves as recommended by the equipment manufacturer.


PACKAGING SIZES

ATROX® 800HT5 is available in 5 or 10 cc EFD or Musashi syringes.

SHIPPING & STORAGE

Material is normally shipped in insulated boxes using dry ice to ensure that the ATROX® 800HT5 maintains all its properties. On receipt, it must be ensured that dry-ice remnants are present in the insulated shipping box. If there is no dry ice, or if the material is not cold, then please contact Alpha Advanced Materials immediately. Exposing to elevated temperatures during shipment and storage will compromise on the performance aspect of the material adversely.

It is recommended to store the syringes of material at -40°C for a maximum shelf life of 6 months. It is recommended that the material be allowed to thaw before usage. Typical thawing times for 5cc and 10cc syringes are presented in chart below. Remove the syringe from freezer and set aside, allowing it to thaw at room temperature, until it reaches room temperature (90 minutes maximum for 30CC syringe). To prevent contamination of unused product, do not return any material to its original container.



To confirm this is the most recent issue, please contact Alpha Advanced Materials

AAM.AlphaAssembly.com

<p>USA 3950 Johns Creek Ct, Suite 300 Suwanee, GA 30024 USA 908.791.2315</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400</p>	<p>Asia 14 Joo Koon Crescent, Singapore 629014 65.6861.0244</p>
---	---	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions.™ Trademark of MacDermid Performance Solutions.
© Platform Specialty Products Corporation and its subsidiaries 2016.